


Certificate Ref: 3000413745

Order Ref: PO-03583
Received: 08/11/2019
Issue Date: 26/11/2019

For the attention of: Leah Hatch
K & S Aerospace Components
Unit 14 Eddystone Road
South Hants Industrial Park
SOUTHAMPTON
Hampshire
SO40 3SA



Lloyd Roper
Metallurgical Technician

BUTT WELDED STAINLESS STEEL SHEET
Material Specification - MSRR 6523

Welded By : J Gooch
Welder ID : KS09
Welding Process : TIG
Filler Rod : MSRR 9500/2
Job Number : 01721

Weld Test

Overall Result Acceptable

Visual Examination

Condition As Welded
Magnification Up to x25
Result Acceptable

Tensile Test

Laboratory Temperature		20 °C
Dimensions	a x b	25.0 x 1.23 mm
Area	So	30.8 mm ²
Maximum Force	Fm	20.56 kN
Tensile Strength	Rm	668 N/mm ²
Tensile Strength	Rm	96.89 ksi
Broke		Clear of weld
Result		Acceptable - providing tensile strength meets the design requirements

Specification*

Specification**



0034

Decision Rule - Zero guard band approach implemented where applicable.
Page 1 of 2

Certificate must not be reproduced, except in full, without the written approval of Keighley Laboratories Limited
Results relate only to item(s) tested.



Certificate Ref: 3000413745

Order Ref: PO-03583
Received: 08/11/2019
Issue Date: 26/11/2019

Bend Test

**Test Piece Pickled in accordance with BS
EN ISO 3651:1998 Method 'A'**

Laboratory Temperature	20 °C
Bend Radius	3 x thickness
Face Bend	Bent 90° without cracking.
Result	Acceptable

Metallographic Examination

Magnification	x50 - x500
Etchant	Ferric Chloride
Section(s) assessed	1
Result	Acceptable

Test Schedule: C.A.A. - British Civil Airworthiness Requirements Chapter A8-10 as applicable.
Test Schedule: Rolls Royce plc. - RPS 912 Issue 18 as applicable.
Test Schedule: British Standard BS ISO 24394:2018 as applicable.

*** END OF DOCUMENT ***



0034

Decision Rule - Zero guard band approach implemented where applicable.
Page 2 of 2

Certificate must not be reproduced, except in full, without the written approval of Keighley Laboratories Limited
Results relate only to item(s) tested.

