

Certificate Ref: 3000413743

Order Ref: PO-03583
Received: 08/11/2019
Issue Date: 26/11/2019

Bend Test

Test Piece Pickled in accordance with BS EN ISO 3651:1998 Method 'A'

Laboratory Temperature 20 °C
Bend Radius 3 x thickness
Face Bend Bent 90° without cracking.
Result Acceptable

Metallographic Examination

Magnification x50 - x500
Etchant Ferric Chloride
Section(s) assessed 1
Result Acceptable

Test Schedule: C.A.A. - British Civil Airworthiness Requirements Chapter A8-10 as applicable.
Test Schedule: Rolls Royce plc. - RPS 912 Issue 18 as applicable.
Test Schedule: British Standard BS ISO 24394:2018 as applicable.

*** END OF DOCUMENT ***

Decision Rule - Zero guard band approach implemented where applicable.

Page 2 of 2

Certificate must not be reproduced, except in full, without the written approval of Keighley Laboratories Limited
Results relate only to item(s) tested.



0034

